

Trovidur® ESA-D

Rigid Polyvinyl Chloride
Röchling Engineering Plastics SE & Co. KG

Message:

- Product characteristics
- Raised impact strength, high cold impact
- High UV and weather resistance
- Excellent printability
- Typical field of application
- Building industry
- Visual communication
- Vacuum forming techniques

General Information			
Features	Excellent Printability		
	Good UV Resistance		
	Good Weather Resistance		
Uses	Building Materials		
	Construction Applications		
Processing Method	Vacuum Forming		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	< 3.0	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	6.0E-5 to 8.0E-5	cm/cm/°C	DIN 53752
Heat Deflection Temperature - Vicat B	74	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Constant	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.020		IEC 60250

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

