

CYCOLOY™ CX2142ME resin

Polycarbonate + ABS

SABIC Innovative Plastics

Message:

CYCOLOY resin grade CX2142ME is an injection moldable PC/ABS blend with Br- and Cl-free flame retardant systems. Key features of good flow, good impact, UL-94 V0 rating at 1.2 mm, and improved chemical resistance to generally used hospital cleaners, make it ideal for a wide variety of applications including enclosures for medical and hospital equipments.

General Information			
UL YellowCard	E45329-546803		
Additive	Flame retardancy		
Features	Chlorine Free		
	Impact resistance, good		
	Good liquidity		
	Good chemical resistance		
	Bromine-free		
Uses	Flame retardancy		
	Shell		
	Medical/nursing supplies		
	Medical equipment		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/2.16 kg)	23	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.20	%	ISO 62
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2900	MPa	ASTM D638
--	2700	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	64.0	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/50

Fracture ³	54.0	MPa	ASTM D638
Fracture	51.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	4.0	%	ASTM D638
Yield	4.0	%	ISO 527-2/50
Fracture ⁵	90	%	ASTM D638
Fracture	90	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2700	MPa	ASTM D790
-- ⁷	2500	MPa	ISO 178
Flexural Stress			
--	100	MPa	ISO 178
Yield, 50.0mm span ⁸	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	15	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	120	J/m	ASTM D256
23°C	600	J/m	ASTM D256
-30°C ¹⁰	10	kJ/m ²	ISO 180/1A
23°C ¹¹	15	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	63.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	94.0	°C	ASTM D648
0.45 MPa, unannealed, 6.40mm	98.0	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	84.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	90.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	84.0	°C	ISO 75-2/Af
Vicat Softening Temperature	102	°C	ASTM D1525, ISO 306/B50, ISO 306/B120 ¹³
Ball Pressure Test (75°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	7.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Thermal Conductivity	0.20	W/m/K	ISO 8302
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.20 mm	V-0		UL 94
2.00 mm	5VB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	82.2 - 87.8	°C
Drying Time	3.0 - 4.0	hr
Drying Time, Maximum	8.0	hr
Suggested Max Moisture	0.040	%
Suggested Shot Size	30 - 80	%
Rear Temperature	221 - 254	°C
Middle Temperature	221 - 266	°C
Front Temperature	243 - 277	°C
Nozzle Temperature	243 - 277	°C
Processing (Melt) Temp	243 - 277	°C
Mold Temperature	60.0 - 82.2	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.038 - 0.076	mm

NOTE

- | | |
|-----|---------------------------|
| 1. | 50 mm/min |
| 2. | Type 1, 50mm/min |
| 3. | Type 1, 50mm/min |
| 4. | Type 1, 50mm/min |
| 5. | Type 1, 50mm/min |
| 6. | 1.3 mm/min |
| 7. | 2.0 mm/min |
| 8. | 1.3 mm/min |
| 9. | 80*10*3 sp=62mm |
| 10. | 80*10*3 |
| 11. | 80*10*3 |
| 12. | 80*10*4 mm |
| 13. | 标准 B (120°C/h), 载荷2 (50N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT