

MAZMID B 153 SP30

Polyamide 6

Mazzaferro Indústria e Comércio de Polímeros e Fibras Ltda.

Message:

MAZMID B 153 SP30 is a Polyamide 6 (Nylon 6) product filled with 30% mineral. It can be processed by injection molding and is available in Latin America.
Typical application: Automotive.
Characteristics include:
Flame Rated
Good Aesthetics
Heat Stabilizer

General Information				
Filler / Reinforcement		Mineral,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Good Surface Finish		
		Heat Stabilized		
		Paintable		
Uses		Automotive Applications		
Appearance		Black		
		Colors Available		
		Grey		
		Natural Color		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.36	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.90 to 1.2	--	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.90 to 1.0	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	110	100		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	5500	2800	MPa	ASTM D638
Tensile Strength	75.0	50.0	MPa	ASTM D638
Tensile Elongation (Break)	6.0	25	%	ASTM D638
Flexural Modulus	5000	2000	MPa	ASTM D790
Flexural Strength	120	70.0	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	50	100	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method

Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	170	--	°C	
1.8 MPa, Unannealed	120	--	°C	
Continuous Use Temperature				
	90.0 to 100	--	°C	
Melting Temperature				
	212 to 214	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+12	--	ohms·cm	ASTM D257
Dielectric Strength	15	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.60 mm)	V-2	--		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

