

VESTAMID® Care ME62-B

Polyether Block Amide

Evonik Industries AG

Message:

VESTAMID® Care ME grades represent a range of flexible polyether block amide (PEBA) resins of varying hardness for processing via extrusion or injection molding. VESTAMID® Care ME materials are available as standard and bonding-modified grades.

VESTAMID® Care ME standard grades have a proven history in catheter applications. Due to their broad range of flexibility, VESTAMID® CareME grades are used in different parts of catheter constructions - may it be the distal end, requiring a low modulus for non-traumatic insertion, or the proximal end, needing a high modulus for force and torque transmission. The advantages at a glance:

- High flexibility & elasticity
- Good rebound properties
- High impact resistance
- High dimensional stability
- High chemical resistance
- High toughness
- Easy processability & colorability
- Free of volatile plasticizers

General Information			
Features	Biocompatible		
	Good Chemical Resistance		
	Good Colorability		
	Good Dimensional Stability		
	Good Flexibility		
	Good Processability		
	Good Toughness		
	High Elasticity		
	High Impact Resistance		
Uses	Medical Devices		
	Medical/Healthcare Applications		
	Tubing		
Agency Ratings	ISO 10993		
	USP 88		
	USP Class VI		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.02	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	64		ISO 868

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	500	MPa	ISO 527-2
Tensile Stress			ISO 527-2/50
Yield, 23°C	42.0	MPa	
50% Strain, 23°C	25.0	MPa	
Tensile Strain (Break, 23°C)	> 200	%	ISO 527-2/50
Tensile Creep Modulus (1000 hr)	200	MPa	ISO 899-1
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	8.0	kJ/m ²	
23°C, Partial Break	100	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	169	°C	ISO 306/A
--	126	°C	ISO 306/B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

