

# Huaфон HF-1190A

Thermoplastic Polyurethane Elastomer (Polyester)

Huaфон Group Co., Ltd.

## Message:

Operation: Injection molding  
Characteristics: Easy processing, Fast de-molding  
Applications: Gardening shoes, Accessories, Fashion shoe sole, etc., Heel life.

General Information			
Features	Good Processability		
Uses	Footwear		
Processing Method	Injection Molding		
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore A)	91	ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	7.80	MPa	ASTM D412
Tensile Strength	29.0	MPa	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Tear Strength	135	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

