

Trovidur® EC

Rigid Polyvinyl Chloride

Röchling Engineering Plastics SE & Co. KG

Message:

- Product Characteristics
- High resistance to acids, lyes and salt solutions
- Fire class B1 to DIN 4102 up to 4mm thickness
- Highly weldable and adherable
- Typical field of application
- Chemical engineering and tank building
- Ventilation manufacturing
- Electrical and electronic industries

General Information			
Features	Acid Resistant		
	Bondability		
	Good Chemical Resistance		
	Weldable		
Uses	Electrical/Electronic Applications		
	Engineered Applications		
	Tanks		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	1.0	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	6.0E-5 to 8.0E-5	cm/cm/°C	DIN 53752
Thermal Conductivity	0.16	W/m/K	DIN 52612
Heat Deflection Temperature - Vicat B	70	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Constant	3.20		IEC 60250
Dissipation Factor (1 MHz)	0.020		IEC 60250

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	V-0		
6.00 mm	V-0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

