APEX® 3311-80NT

Flexible Polyvinyl Chloride

Teknor Apex Company

Message:

APEX® 3311-80NT is a Flexible Polyvinyl Chloride material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion.

Important attributes of APEX® 3311-80NT are:

Plasticized

Sterilizable

Typical applications include:

Consumer Goods

Hose/Tubing

Medical/Healthcare

| General Information | | | |
|--------------------------------------|---------------------------------|-------|-------------|
| Additive | Plasticizer | | |
| Features | Ethylene Oxide Sterilizable | | |
| | Non-DEHP Plasticizer | | |
| | | | |
| Uses | Medical/Healthcare Applications | | |
| | Toys | | |
| | Tubing | | |
| | | | |
| Appearance | Natural Color | | |
| | Opaque | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.35 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 15 sec) | 80 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| Break | 15.8 | MPa | |
| 100% Strain | 8.55 | MPa | |
| Tensile Elongation (Break) | 360 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -28.0 | °C | ASTM D746 |
| Extrusion | Nominal Value | Unit | |
| Melt Temperature | 179 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2