## Spartech Polycom SC7A21-3000

Polycarbonate + PBT

Spartech Polycom

## Message:

Spartech SC7A21-3000 is an impact modified, PC/PBT alloy for injection molding applications.

The alloys bridge desirable characteristics of both resins. They benefit from the flow characteristics of PBT, and the high heat distortion temperature is influenced by the polycarbonate fraction. The alloys approach the toughness of polycarbonate without the thickness sensitivity.

A very versatile product for a wide variety of applications, Spartech SC7A21-3000 is recommended for industrial, transportation, sporting goods and electrical/electronic applications.

| General Information        |                                    |          |             |  |  |
|----------------------------|------------------------------------|----------|-------------|--|--|
| Additive                   | Impact modifier                    |          |             |  |  |
| Features                   | Impact modification                |          |             |  |  |
|                            | Impact resistance, good            |          |             |  |  |
|                            | Good liquidity                     |          |             |  |  |
|                            | Heat resistance, high              |          |             |  |  |
|                            | Good toughness                     |          |             |  |  |
| Uses                       | Electrical/Electronic Applications |          |             |  |  |
|                            | Industrial application             |          |             |  |  |
|                            | Application in Automobile Field    |          |             |  |  |
|                            | Sporting goods                     |          |             |  |  |
| Appearance                 | Available colors                   |          |             |  |  |
|                            | Natural color                      |          |             |  |  |
| Forms                      | Particle                           |          |             |  |  |
| Processing Method          | Injection molding                  |          |             |  |  |
| Physical                   | Nominal Value                      | Unit     | Test Method |  |  |
| Melt Mass-Flow Rate (MFR)  | 24                                 | g/10 min | ASTM D1238  |  |  |
| Mechanical                 | Nominal Value                      | Unit     | Test Method |  |  |
| Tensile Strength (23°C)    | 55.2                               | МРа      | ASTM D638   |  |  |
| Flexural Modulus (23°C)    | 2140                               | MPa      | ASTM D790   |  |  |
| Flexural Strength (23°C)   | 101                                | MPa      | ASTM D790   |  |  |
| Impact                     | Nominal Value                      | Unit     | Test Method |  |  |
| Notched Izod Impact (23°C) | 690                                | J/m      | ASTM D256   |  |  |
| Injection                  | Nominal Value                      | Unit     |             |  |  |
| Drying Temperature         | 87.8                               | °C       |             |  |  |
| Drying Time                | 2.0 - 4.0                          | hr       |             |  |  |
| Rear Temperature           | 249 - 282                          | °C       |             |  |  |
| Middle Temperature         | 254 - 288                          | °C       |             |  |  |

| Front Temperature      | 260 - 293   | °C |  |
|------------------------|-------------|----|--|
| Nozzle Temperature     | 274 - 302   | °C |  |
| Processing (Melt) Temp | 274 - 302   | °C |  |
| Mold Temperature       | 82.2 - 93.3 | °C |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

