# FLEXCHEM<sup>™</sup> 6052

## Flexible Polyvinyl Chloride

### **Colorite Polymers**

#### Message:

FLEXCHEM<sup>™</sup> 6052 is a Flexible Polyvinyl Chloride product. It can be processed by extrusion or injection molding and is available in Asia Pacific, Europe, or North America. Typical application: Medical/Healthcare. Characteristics include: Plasticized Sterilizable Good Flexibility Good Mold Release Wear Resistant

| General Information           |                             |       |             |
|-------------------------------|-----------------------------|-------|-------------|
| Additive                      | Plasticizer                 |       |             |
| Features                      | Durable                     |       |             |
|                               | Ethylene Oxide Sterilizable |       |             |
|                               | Good Flexibility            |       |             |
|                               | Good Mold Release           |       |             |
|                               | Plasticized                 |       |             |
|                               | Radiation Sterilizable      |       |             |
|                               |                             |       |             |
| Agency Ratings                | USP Class VI                |       |             |
| Processing Method             | Extrusion                   |       |             |
|                               | Injection Molding           |       |             |
|                               |                             |       |             |
| Physical                      | Nominal Value               | Unit  | Test Method |
| Specific Gravity              | 1.17                        | g/cm³ | ASTM D792   |
| Hardness                      | Nominal Value               | Unit  | Test Method |
| Durometer Hardness (Shore A)  | 60                          |       | ASTM D2240  |
| Mechanical                    | Nominal Value               | Unit  | Test Method |
| Tensile Modulus - 100% Secant | 5.03                        | MPa   | ASTM D638   |
| Tensile Strength              | 12.4                        | MPa   | ASTM D638   |
| Tensile Elongation (Break)    | 320                         | %     | ASTM D638   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

