

Tenogel® ABS A3 G30 UV PRTA010 AB320

Acrylonitrile Butadiene Styrene
Petropol Industry and Trade of Polymers LTDA

Message:

Tenogel® ABS A3 G30 UV PRTA010 AB320 is an Acrylonitrile Butadiene Styrene (ABS) material filled with 30% glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding.
Important attributes of Tenogel® ABS A3 G30 UV PRTA010 AB320 are:
Flame Rated
Good Dimensional Stability

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Good Dimensional Stability		
	Good Strength		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0 to 15	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10 to 0.40	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	100	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	6300	MPa	ASTM D790
Flexural Strength	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	78	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	170	°C	ASTM D648
Vicat Softening Temperature	150	°C	ASTM D1525
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	190 to 240	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

