

# Sylvin 8200-85UV Red 6259

Polyvinyl Chloride  
Sylvin Technologies Incorporated

Message:

Sylvin 8200-85UV Red 6259 Is A Vinyl Compound Formulated For Extrusion Applications That Require Outdoor UV Stability, Excellent Ozone Resistance, Good Abrasion Resistance, Good Low Temperature Properties, And Ease Of Processing.

General Information	
Features	Good UV resistance
	Workability, good
	Good wear resistance
	Ozone resistance
	Low temperature resistance
	General
Uses	Industrial application
	General
Appearance	Red
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	85		ASTM D2240
Shaw A, 10 seconds	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	18.3	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	87.6	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	168 - 179	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

