

Ultrason® E 2020 P SR

Polyethersulfone

BASF Corporation

Message:

Polyethersulfone flakes, e.g. for membrane applications, coatings and resin modification, containing min. 50% of OH-endgroups. The product is soluble in N-methyl-pyrrolidone (NMP) and N,N-Dimethylacetamide (DMAc). This type is not suitable for thermoplastic moulding.

General Information			
Uses	Coating Applications		
	Membranes		
	Plastics Modification		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Flakes		
Resin ID (ISO 1043)	PESU		
Physical	Nominal Value	Unit	Test Method
Apparent Density	0.30	g/cm³	ISO 60
Water Absorption (Equilibrium, 23°C, 50% RH)	1.0	%	ISO 62
Viscosity Number ¹	59.0	cm³/g	ISO 307
Molecular Weight - GPC in DMAc ²	55000	g/mol	
Mw/Mn - GPC in DMAc ³	2.70		
NOTE			
1.	in 0,01 g/ml Phenol/1,2, ortho-Dichlorbenzol, 1:1		
2.	PMMA standard		
3.	PMMA standard		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT