

# Pro-fax RP329N

Polypropylene Random Copolymer  
LyondellBasell Industries

Message:

Pro-fax RP329N antiblock-formulated polypropylene random copolymer is available in pellet form. This resin is typically used in cast film applications and offers exceptional clarity and gloss as well as improved cold temperature impact resistance and broader heat seal range compared to homopolymer. For regulatory compliance information see Pro-fax RP329N Product Stewardship Bulletin (PSB).

General Information			
Additive	High Antiblock		
Features	Good Heat Seal		
	Good Processability		
	High Antiblocking		
	High Clarity		
	High Gloss		
	Low Temperature Impact Resistance		
	Opticals		
	Random Copolymer		
Uses	Bags		
	Cast Film		
	Film		
	Food Packaging		
	Packaging		
	Pouches - Flexible Packaging		
	Stretch Wrap		
Forms	Pellets		
Processing Method	Cast Film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm <sup>3</sup>	ASTM D792B
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	28.0	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	965	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	43	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method


Deflection Temperature Under Load (0.45 MPa, Unannealed)	74.0	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT