

Torayca® NX85T-10A

Polycarbonate
Toray Resin Company

Message:

Torayca® NX85T-10A is a Polycarbonate (PC) product filled with 8.0% carbon fiber. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
Flame Rated
Flame Retardant

General Information			
Filler / Reinforcement	Carbon Fiber,8.0% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Part Marking Code	>PC-CF10<		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	26	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 3.00 mm ¹	0.25 to 0.55	%	
Flow : 3.00 mm ²	0.25	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (23°C)	56.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2
Flexural Modulus (23°C)	6400	MPa	ISO 178
Flexural Stress (23°C)	111	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.3	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	121	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+3	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
NOTE			
1.	80x80x3		
2.	80x80x3mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

