Braskem PP TI2350C

High Crystallinity Polypropylene

Braskem America Inc.

Message:

Sub-group

High Crystallinity Copolymer

Description

Highly crystalline homopolymer phase, very high molecular weight EPR phase, very high flexural modulus, reduced emissions, reduced gels, high melt

Applications

Suggested uses include compounding

General Information			
Features	Copolymer		
	Food Contact Acceptable		
	Highly Crystalline		
	Low Emissions		
	Low Gel		
	Ultra High Molecular Weight		
Uses	Compounding		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Compounding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	40	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Injection Molded)	31.7	MPa	ASTM D638
Tensile Elongation ² (Yield, Injection Molded)	6.0	%	ASTM D638
Flexural Modulus - 1% Secant ³ (Injection Molded)	1590	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Injection Molded)	53	J/m	ASTM D256A
NOTE			
1.	51 mm/min		
2.	51 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

