

DINAPLEN® PPH1S20 M203-4106

Polypropylene Homopolymer

Grupo Repol

Message:

DINAPLEN® PPH1S20 M203-4106 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 20% mineral. It is available in Europe. Primary characteristic: homopolymer.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Homopolymer		
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress (Break)	35.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	4.0	%	
Break	8.5	%	
Flexural Modulus	1600	MPa	ISO 178
Flexural Stress	45.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	40	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT