

Polytech & Net VC910

Ethylene Vinyl Acetate Copolymer

Polytech & Net GmbH

Message:

Hot Melt Adhesive

General Information			
Uses	Adhesives		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR)	400	g/10 min	ASTM D1238
Vinyl Acetate Content	28.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	18		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	< 40.0	°C	ASTM D1525
Peak Melting Temperature	65.0	°C	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT