apilon 52® FA-56E

Thermoplastic Polyurethane Elastomer (Polyester)

API SpA

Message:

apilon 52®FA-56E is a thermoplastic polyurethane elastomer (polyester) (TPU-polyester) product. It can be processed by injection molding and is available in Europe. apilon 52®FA-56E application areas include engineering/industrial accessories, electrical/electronic applications, electrical appliances, tools and home applications.

Features include: high liquidity environmental protection/green Good flexibility

low temperature resistance

General Information

Features	No frost							
	Recyclable materials							
	Good flexibility High liquidity Low temperature resistance							
					Uses	Handle		
Wheels								
Conveyor belt repair								
Electrical/Electronic Applications								
Electrical appliances								
Washer								
Power/other tools								
Pipe fittings								
Household goods								
Sporting goods								
Coating application								
Footwear								
Processing Method	Injection molding							
Physical	Nominal Value	Unit	Test Method					
Specific Gravity	1.17	g/cm³	ASTM D792					
Hardness	Nominal Value	Unit	Test Method					
Durometer Hardness (Shore A, 15 sec)	54		ASTM D2240					
Mechanical	Nominal Value	Unit	Test Method					
Tensile Strength			ASTM D638					
	18.0	MPa	ASTM D638					
100% strain	2.00	MPa	ASTM D638					

300% strain	3.00	MPa	ASTM D638
Tensile Elongation (Break)	900	%	ASTM D638
Abrasion Resistance	60.0	mm³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	50.0	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	80 - 100	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	185 - 200	°C	
Front Temperature	190 - 215	°C	
Nozzle Temperature	200 - 230	°C	
Mold Temperature	30 - 60	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Slow-Moderate		
NOTE			
1.	With Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

