

4LEX® 10F20000

Polycarbonate
4Plas

Message:

4LEX 10F20000 is a MFI 15 to 18 Unfilled Polycarbonate

General Information			
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2160	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	63.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	120	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	65	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	133	°C	ISO 75-2/B
1.8 MPa, not annealed	133	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/B
Melting Temperature ²	150	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Dielectric Constant (1 MHz)	2.90		ASTM D150
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature (2.00 mm)	950	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	260 - 300	°C	

Mold Temperature	80.0 - 100	°C
Injection Rate	Moderate-Fast	
Holding Pressure	60.0 - 120	MPa
Screw Speed	< 200	rpm

Injection instructions

Feed Throat Temperature: 60 - 80 °CBack Pressure: Low

NOTE

- | | |
|----|----------|
| 1. | 24 Hrs |
| 2. | 10 K/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT