

Ferro PP TPP40AJ26UL-TN

Polypropylene
Ferro Corporation

Message:

Ferro PP TPP40AJ26UL-TN is a Polypropylene material filled with 40% talc. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Appearance	Tan		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	76		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.5	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength (Yield)	56.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	138	°C	
1.8 MPa, Unannealed	87.8	°C	
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	204 to 210	°C	
Middle Temperature	210 to 213	°C	
Front Temperature	213 to 216	°C	
Nozzle Temperature	216 to 218	°C	
Mold Temperature	43.3 to 54.4	°C	
Back Pressure	0.138 to 0.345	MPa	
Screw Speed	100 to 150	rpm	
Clamp Tonnage	2.8 to 4.1	kN/cm ²	

Screw L/D Ratio	20.0:1.0
Screw Compression Ratio	2.0:1.0

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

