

Cabofor® 28 V0 BIANCO 0199

Polycarbonate
SO.F.TER. SPA

Message:
Flame retardant polycarbonate grade, medium fluidity, good mechanical properties

General Information			
Features	Flame Retardant		
	Medium Flow		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage	0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	70.0	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	450	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	140	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Needle Flame Test	Pass		IEC 60695-11-5
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0	hr	
Rear Temperature	240	°C	
Middle Temperature	260	°C	
Front Temperature	280	°C	
Mold Temperature	100 to 120	°C	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

