

# TOYOBO Urethane A1071D

Polyurethane (Polybutyleneadipate)

TOYOBO America, Inc.

Message:

TOYOBO Urethane A1071D is a polyurethane (polybutylene adipate)(PUR-butyl) product. It can be processed by injection molding and is available in North America.

General Information			
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	71		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	51.0	MPa	ASTM D638
100% strain	25.5	MPa	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Taber Abrasion Resistance (1000 Cycles)	80.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	294	kN/m	ASTM D624
Compression Set	45	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-65.0	°C	ASTM D746
Vicat Softening Temperature	138	°C	ASTM D1525
Additional Information			

Taber Abrasion Resistance, H22, 1000 cycles: 80 mgBrittle Temperature, ASTM D746: < -65 °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT