

TEKAMID™ H14HT

Acrylonitrile Butadiene Styrene + Nylon

Mando Advanced Materials Co., Ltd.

Message:

TEKAMID™ H14HT is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) product. It is available in Asia Pacific.

Characteristics include:

Flame Rated

Good Toughness

General Information			
Features	Ultra High Toughness		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm ³	ASTM D792
Molding Shrinkage ¹			ASTM D955
Flow	0.70	%	
Across Flow	0.70	%	
Water Absorption (24 hr)	0.90	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	51.0	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	2060	MPa	ASTM D790
Flexural Strength	76.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	80.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	220 to 240	°C	
Mold Temperature	60.0 to 80.0	°C	
NOTE			

1. 60°C Mold Temperature

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

