

Exxtral™ Performance Polyolefin BMU130

Polypropylene, Compounded (TPO)

ExxonMobil Chemical

Message:

A special thermoplastic polyolefin resin with good rigidity/toughness balance, suitable for automotive exterior parts (such as bumper panels).

General Information			
Features	Equilibrium rigidity/toughness		
	Impact resistance, high		
	Good UV resistance		
	Low temperature impact resistance		
	Good weather resistance		
	ductility		
Uses	Car anti-collision bar		
	Automotive exterior parts		
	Car exterior decoration		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)	19.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant (23°C)	1200	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	15.1	MPa	ISO 527-2
Fracture	11.6	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	4.3	%	ISO 527-2
Fracture	79	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C, complete fracture	8.0	kJ/m ²	ISO 179
-20°C, complete fracture	11	kJ/m ²	ISO 179
23°C, local fracture	65	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	47.0	°C	ISO 75-2/A

Legal statement

本产品不宜在与食品接触的应用中使用.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

