

ARMAMID® PA MN M 60-1

Polyamide 6

Poly Plastic

Message:

ARMAMID® PA MN M 60-1 is a Polyamide 6 (Nylon 6) product filled with mineral. It is available in Europe.

General Information			
Filler / Reinforcement	Mineral		
Physical	Nominal Value	Unit	Test Method
Density	2.05	g/cm ³	
Molding Shrinkage	0.20 to 0.50	%	
Water Absorption (23°C, 24 hr)	1.0	%	ISO 62
Mechanical	Nominal Value	Unit	
Tensile Stress (Yield)	64.0	MPa	
Flexural Modulus (23°C)	4500	MPa	
Flexural Stress	80.0	MPa	
Impact	Nominal Value	Unit	
Charpy Unnotched Impact Strength (20°C)	No Break		
Thermal	Nominal Value	Unit	
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	°C	
Melting Temperature	216	°C	
Electrical	Nominal Value	Unit	
Surface Resistivity			
-- 1	1.0E+13	ohms	
-- 2	1.0E+15	ohms	
Volume Resistivity			
-- 3	1.0E+15	ohms · cm	
-- 4	1.0E+17	ohms · cm	
Electric Strength			
-- 5	14 to 17	kV/mm	
-- 6	21 to 24	kV/mm	
NOTE			
1.	Wet		
2.	Dry		
3.	Wet		
4.	Dry		
5.	Wet		
6.	Dry		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

