

ESTACARB PC 2020 GF V0

Polycarbonate

Cossa Polimeri S.r.l.

Message:

ESTACARB PC 2020 GF V0 is a polycarbonate (PC) product containing a 10% glass fiber reinforced material. It is available in Europe. The application fields of ESTACARB PC 2020 GF V0 include electrical/electronic applications and engineering/industrial accessories.

Features include:

flame retardant/rated flame

Flame Retardant

Good processability

Hard

Good dimensional stability

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Good UV resistance		
	Workability, good		
	Good liquidity		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Engineering accessories		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 - 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	64.0	MPa	ASTM D638
Tensile Elongation (Yield)	3.5	%	ASTM D638
Flexural Modulus	3600	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	70	J/m	ASTM D256
23°C	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	150	°C	ASTM D1525 ¹
--	147	°C	ASTM D1525 ²

Ball Indentation Temperature	135	°C	IEC 60598-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		UL 94
3.20 mm	V-0		UL 94
Glow Wire Ignition Temperature	960	°C	IEC 60695-2-13

Additional Information

Note: Ball Indention Temperature, IEC 60598-1 was tested in accordance with IEC 695-1-2.Ball Pressure Test, IEC 335-1, 105°C: yes

Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	2.0	hr
Processing (Melt) Temp	250 - 270	°C
Mold Temperature	60.0 - 90.0	°C
Injection Rate	Moderate	

Injection instructions

Injection Pressure: Medium

NOTE

1. 压力1 (10N)
2. 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT