

Galoo GP-PP-125T40

Polypropylene

Galoo Plastics

Message:

40% talcum modified black colored polypropylene compound

This grade is also available in a UV stabilized version and/or specific color.

General Information			
Filler / Reinforcement	Talc filler, 40% filler by weight		
Recycled Content	Yes		
Appearance	Black		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.23 - 1.27	g/cm ³	Internal method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10 - 14	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.5	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	5.0	kJ/m ²	ISO 180
Additional Information	Nominal Value	Unit	Test Method
Charge Rate	37 - 43	%	Internal method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT