

Sumiliteresin® PR-50064

Phenolic
SBHPP

Message:

SUMILITERESIN® PR-50064 is a Powder novolac resin based on Phenolic Novolac polymer. It is supplied in the form of Powder for Friction Materials.

General Information		
Forms	Powder	
Physical	Nominal Value	Unit
Spiral Flow ¹	2.10	cm
Thermal	Nominal Value	Unit
Melting Temperature	90.0	°C
Uncured Properties	Nominal Value	Unit
Gel Time (150°C)	0.80	min
NOTE		
1.	Mold temperature: 125°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT