

SCHULAMID® 6 MV 14 FR 4 K1681

Polyamide 6
A. Schulman Europe

Message:
Medium viscosity flame-retardant Polyamide 6 grade (V-2); without PBDE

General Information				
UL YellowCard		E344659-101038371	E86615-252170	E188844-102210964
Features		Flame Retardant Medium Viscosity		
UL File Number		E86615		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.26	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	160	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3800	1250	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	70.0	35.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.0	24	%	ISO 527-2/1A/50
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	3.0	--	kJ/m ²	
23°C	4.0	18	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	48	--	kJ/m ²	
23°C	49 kJ/m ²	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	186	--	°C	ISO 75-2/Bf
1.8 MPa, Unannealed	76.0	--	°C	ISO 75-2/Af
Vicat Softening Temperature				
--	217	--	°C	ISO 306/A50
--	202	--	°C	ISO 306/B50
Ball Pressure Test (200°C)	Pass	--		IEC 60695-10-2

RTI Elec				UL 746
0.380 mm	130	--	°C	
0.750 mm	130	--	°C	
1.50 mm	130	--	°C	
3.00 mm	130	--	°C	
RTI Imp				UL 746
0.380 mm	75.0	--	°C	
0.750 mm	90.0	--	°C	
1.50 mm	100	--	°C	
3.00 mm	100	--	°C	
RTI Str				UL 746
0.380 mm	100	--	°C	
0.750 mm	110	--	°C	
1.50 mm	120	--	°C	
3.00 mm	120	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index	300	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.380 mm	PLC 0	--		
0.750 mm	PLC 0	--		
1.50 mm	PLC 0	--		
3.00 mm	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746
0.380 mm	PLC 4	--		
0.750 mm	PLC 4	--		
1.50 mm	PLC 2	--		
3.00 mm	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.380 mm, Self-Extinguishing	0.0	--	mm/min	
0.750 mm, Self-Extinguishing	0.0	--	mm/min	
1.50 mm, Self-Extinguishing	0.0	--	mm/min	
3.00 mm, Self-Extinguishing	0.0	--	mm/min	
Flame Rating				UL 94, IEC 60695-11-10, -20
0.380 mm	V-2	--		
0.750 mm	V-2	--		
1.50 mm	V-2	--		

3.00 mm	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.380 mm	850	--	°C	
0.750 mm	850	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.380 mm	825	--	°C	
0.750 mm	825	--	°C	
1.50 mm	825	--	°C	
3.00 mm	825	--	°C	
Oxygen Index	23	--	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT