# Gallonprene® GP540-8505C

## Thermoplastic Elastomer

### Shenzhen Sungallon Rubber & Plastic Corporation Limited

#### Message:

Gallonprene® GP540-8505C is a Thermoplastic Elastomer (TPE) product. It can be processed by extrusion or profile extrusion and is available in Africa & Middle East, Asia Pacific, or Latin America. Applications of Gallonprene® GP540-8505C include hose/tubing and wire & cable. Characteristics include: REACH Compliant RoHS Compliant Good Aesthetics Halogen Free

| General Information                     |                           |          |             |
|---|---------------------------|----------|-------------|
| Features                                | Good Surface Finish       |          |             |
|   | Halogen Free              |          |             |
|   | High Elasticity           |          |             |
|   |                           |          |             |
| Uses                                    | Profiles                  |          |             |
|   | Tubing                    |          |             |
|   | Wire & Cable Applications |          |             |
|   |                           |          |             |
| Agency Ratings                          | EC 1907/2006 (REACH)      |          |             |
| RoHS Compliance                         | RoHS Compliant            |          |             |
| Appearance                              | White                     |          |             |
| Processing Method                       | Extrusion                 |          |             |
|   | Profile Extrusion         |          |             |
|   |                           |          |             |
| Physical                                | Nominal Value             | Unit     | Test Method |
| Specific Gravity                        | 1.03                      | g/cm³    | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (200°C/10.0   |                           |          |             |
| kg)                                     | 6.0                       | g/10 min | ASTM D1238  |
| Hardness                                | Nominal Value             | Unit     | Test Method |
| Durometer Hardness (Shore A, 23°C)      | 85                        |          | ASTM D2240  |
| Elastomers                              | Nominal Value             | Unit     | Test Method |
| Tensile Strength <sup>1</sup> (Break)   | 10.0                      | MPa      | ASTM D412   |
| Tensile Elongation <sup>2</sup> (Break) | 600                       | %        | ASTM D412   |
| Extrusion                               | Nominal Value             | Unit     |             |
| Cylinder Zone 1 Temp.                   | 160 to 180                | °C       |             |
| Cylinder Zone 2 Temp.                   | 170 to 190                | °C       |             |
| Cylinder Zone 3 Temp.                   | 180 to 200                | °C       |             |
| NOTE                                    |                           |          |             |
| 1.                                      | 500 mm/min                |          |             |

#### 500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

