

PERCOM® KHS09

Polypropylene Homopolymer

A. Schulman Europe

Message:

PERCOM® KHS09 is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of PERCOM® KHS09 are:

- Flame Rated
- RoHS Compliant
- Homopolymer

General Information			
UL YellowCard	E132739-222170		
Features	General Purpose		
	Homopolymer		
Uses	General Purpose		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage	1.5 to 2.0	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	60		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	30.0	MPa	ISO 527-2
Tensile Strain (Break)	10	%	ISO 527-2
Flexural Modulus	1550	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.0	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	96.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	56.0	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/A50
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

