MTEGRITY™ LLDPE LL107AH

Linear Low Density Polyethylene

M. Holland Company

Message:

Linear Low Density Polyethylene Super Hexene No Slip High Antiblock Liners Industrial Packaging

| General Information | | | |
|---------------------------|------------------------|----------|-------------|
| Additive | High caking resistance | | |
| Features | Low density | | |
| | High caking resistance | | |
| | hexene comonomer | | |
| | | | |
| Uses | Packaging | | |
| | Lining | | |
| | | | |
| Forms | Particle | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.916 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) | 0.75 | g/10 min | ASTM D1238 |
| Films | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D882 |
| MD: Break, 25 µm | 40.7 | MPa | ASTM D882 |
| TD: Break, 25 µm | 33.1 | MPa | ASTM D882 |
| Tensile Elongation | | | ASTM D882 |
| MD: Break, 25 µm | 650 | % | ASTM D882 |
| TD: Break, 25 µm | 950 | % | ASTM D882 |
| Dart Drop Impact (25 µm) | 550 | g | ASTM D1709 |
| Elmendorf Tear Strength | | | ASTM D1922 |
| MD : 25 µm | 400 | g | ASTM D1922 |
| TD : 25 μm | 700 | g | ASTM D1922 |
| Additional Information | | | |

* Film properties based on 1 mil film with 3:1 BUR.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

