

Petlon R-Prime PET Jazz 100

Polyethylene Terephthalate

Petlon Polymers Ltd

Message:

100% Post Industrial Recycled, Polyester Compound for Black Applications.

Processing Method: Fibre Spinning, Packaging and Strap Manufacture

General Information	
Recycled Content	Yes, 100%
Uses	Fibers
	Packaging
	Strapping
Appearance	Black
Forms	Granules
Processing Method	Continuous Filament/Spinning
	Extrusion

Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Intrinsic Viscosity	0.60 to 0.70		Internal Method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	258	°C	DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	140	°C	
Drying Time	> 4.0	hr	
Melt Temperature	260 to 290	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT