

Lucky Enpla LGF1150

Polycarbonate

Lucky Enpla Co LTD

Message:

Lucky Enpla LGF1150 is a polycarbonate (PC) product that contains 15% glass fiber reinforced materials. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region. Typical application areas are: electrical/electronic applications. The main characteristics are: wear resistance.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 15% filler by weight		
Features	Good wear resistance		
Uses	Electrical/Electronic Applications		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	88.3	MPa	ASTM D638
Flexural Modulus ²	4410	MPa	ASTM D790
Flexural Strength ³	142	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (3.18 mm)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	142	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Rear Temperature	280 - 300	°C	
Middle Temperature	290 - 310	°C	
Front Temperature	290 - 310	°C	
Nozzle Temperature	280 - 310	°C	
Mold Temperature	90.0 - 110	°C	
Back Pressure	1.96 - 3.92	MPa	
Screw Speed	60 - 80	rpm	
Injection instructions			
Resin Temperature: 290-310°C Injection Pressure (1st Pressure): 700-1200 kg/cm ² Injection Pressure (2nd Pressure): 400-800 kg/cm ²			

NOTE

1.	10 mm/min
2.	5.0 mm/min
3.	5.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

