

Propafilm™ RXD110

Polypropylene Alloy

Innovia Films Ltd.

Message:

Barrier Coated Film
Biaxially oriented polypropylene (BOPP) film coated on both sides with an aqueous dispersion of polyvinylidene chloride (PVdC) copolymer.
RXD110/130/140 are recommended for use in plain and printed overwrapping applications in the cookie and bakery industries. Also suited for use as a single web or in laminate structures for medium to large packs on form-fill-seal machines.

General Information			
Features	Antistatic		
	Excellent Printability		
	Flavor & Aroma Barrier		
	Food Contact Acceptable		
	Gas Barrier		
	Good Impact Resistance		
	Good Weather Resistance		
	Low Moisture Vapor Transmission		
	Low Temperature Impact Resistance		
	Machinable		
	Moisture Barrier		
	Puncture Resistant		
Uses	Bi-axially Oriented Film		
	Food Service Applications		
	Laminates		
	Packaging		
Forms	Film		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage			Internal Method
Flow : 121°C, 1 min	4.0	%	
Flow : 129°C, 1 min	7.0	%	
Across Flow : 129°C, 1 min	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.25		
vs. Itself - Static	0.25		
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	2800	µm	
Seal Strength ¹	0.14	N/mm	Internal Method

Seal Initiation Temperature ²	93.3 to 146	°C	Internal Method
Oxygen Permeability (25°C, 0% RH)	0.38	cm ³ ·mm/m ² /atm/24 hr	ASTM F1927
Water Vapor Transmission Rate (38°C, 90% RH)	4.0	g/m ² /24 hr	ASTM F1770
Yield	39.6	m ² /kg	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	110		ASTM D2457
Haze ³	2.0	%	ASTM D1003
NOTE			
1.	2secs; 15psi		
2.	2secs; 15psi		
3.	Wide angle; 2.5°		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

