

SUPREME GPPS SC203L

General Purpose Polystyrene
Supreme Petrochem Ltd.

Message:
This grade is for intricate molding.

General Information			
Features	Food Contact Acceptable		
	High Clarity		
	Medium Flow		
Uses	Household Goods		
	Medical/Healthcare Applications		
Agency Ratings	FDA 21 CFR 177.1640		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	8.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	46.1	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	2750	MPa	ASTM D790
Flexural Strength	58.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	20	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	83.0	°C	ASTM D648
Vicat Softening Temperature	100	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

