

TEREZ PC 1008 schwarz

Polycarbonate
TER HELL PLASTIC GMBH

Message:
PC, good flowability, including release agent.
Especially suitable for manufacturing of thinwalled injection moulding parts.

General Information			
Additive	Mold Release		
Features	Good Flow		
Uses	Thin-walled Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	130	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT