

INFUSE™ 9107

Olefin Block Copolymer

The Dow Chemical Company

Message:

INFUSE™ 9107 Olefin Block Copolymer is a lower density higher performance olefin copolymer that can be widely used in TPE applications where higher service temperature requirements are needed. INFUSE 9107 also provides high filler loading capability and gives good elastic recovery.

Main Characteristics:

High upper service temperature performance

Highly flexible with good elastic recovery

Fast set up times for processability

General purpose elastomer

Excellent for compounds and blends

Talc dusted

Complies with:

EU, No 10/2011

U.S. FDA FCN 424

Consult the regulations for complete details.

General Information			
Agency Ratings	EU No 10/2011		
	FDA FCN 424		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.866	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, Compression Molded)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant (Compression Molded)	1.61	MPa	ASTM D638
Tensile Strength (Break, Compression Molded)	5.10	MPa	ASTM D638
Tensile Elongation (Break, Compression Molded)	600	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	11.0	MPa	ASTM D412
Tensile Elongation (Break)	1600	%	ASTM D412
Tear Strength	27.0	kN/m	ASTM D624
Compression Set			ASTM D395
21°C	16	%	
70°C	49	%	
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	121	°C	Internal Method

TMA ¹ (1.00 mm)	66	°C	Internal Method
NOTE			

1. 1N, 5°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

