

# ICORENE® N1007

Ethylene Vinyl Acetate Copolymer  
ICO Polymers EMEA, A Division of A. Schulman

Message:

ICORENE® N1007 is a premium copolymer of ethylene vinyl acetate specifically designed for the preparation of masterbatch. The powder form can achieve better colour developments or additive dispersion in a masterbatch than the pellet form. The vinyl acetate content is about 14 %. Maximum processing temperature 240°C. .

General Information			
Additive	Heat Stabilizer		
Features	Copolymer		
	Dispersible		
	Good Colorability		
	Heat Stabilized		
Uses	Masterbatch		
Agency Ratings	EU Food Contact, Unspecified Rating		
	FDA Food Contact, Unspecified Rating		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density	0.934	g/cm <sup>3</sup>	Internal Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Vinyl Acetate Content	14.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	51.0	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	61.0	°C	ASTM D1525
Peak Melting Temperature	88.0	°C	ASTM D3418
Injection	Nominal Value	Unit	
Processing (Melt) Temp	> 240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

