

Latimass 82-06 D030

Polyamide 12

LATI S.p.A.

Message:

Specific density compound based on Polyamide 12 (PA 12).

General Information			
Physical	Nominal Value	Unit	Test Method
Density	3.45	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.70 to 1.0	%	
Flow : 2.00 mm	0.70 to 1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9700	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/5
Yield, 23°C	45.0	MPa	
Break, 23°C	40.0	MPa	
Tensile Strain			ISO 527-2/5
Yield, 23°C	2.0	%	
Break, 23°C	2.5	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C, 3.20 mm)	70	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	155	°C	ISO 75-2/B
1.8 MPa, Unannealed	90.0	°C	ISO 75-2/A
Vicat Softening Temperature	165	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Rate	Moderate		
NOTE			

1. at 60 Mpa of cavity pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT