

# Daelim Po1y® PP-241

Polypropylene Impact Copolymer

DAELIM INDUSTRIAL CO., LTD.

## Message:

Daelim Po1y®PP-241 is a polypropylene impact copolymer (PP Impact Copoly) product. It can be processed by injection molding and is available in the Asia-Pacific region. Daelim Po1y®PP-241 application areas include electrical/electronic applications, home applications and containers.

Features include:

Copolymer

anti-warping

Good stiffness

Good toughness

Impact resistance

General Information			
Features	Block Copolymer		
	Low warpage		
	Rigid, good		
	Low temperature impact resistance		
	Good toughness		
	Narrow molecular weight distribution		
Uses	Electrical/Electronic Applications		
	Household goods		
	Container		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	87		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Yield)	20	%	ASTM D638
Flexural Modulus	1230	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	39	J/m	ASTM D256
23°C	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	105	°C	ASTM D648
Vicat Softening Temperature	150	°C	ASTM D1525
Additional Information			

Accelerated Oven Aging in Air, ASTM D3012, Forced Circulation at 150°C: 360 hours

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT