Shin-Etsu Elastomer KEG-2000-70A/B

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Message:

Shin-Etsu KEG2000-70 is a fast cure type liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. The viscosity of KEG2000-70 is low enough to allow easy pumping through most injection molding systems. High tear strength Rapid cure time at elevated temperature Long pot life at room temperature Typical Applications O-Rings Diaphragms Capping Rubber Rollers Connector packaging Other electrical parts ClassVI certification

| General Information | | |
|--------------------------------|--------------------------------|-------|
| Features | Low viscosity | |
| | Workability, good | |
| | Fast curing | |
| | Good tear strength | |
| | | |
| Uses | Electrical components | |
| | Diaphragm | |
| | Roller | |
| | Shield | |
| | Connector | |
| | | |
| Agency Ratings | FDA not rated | |
| | USP Class VI | |
| | | |
| Processing Method | Liquid Injection Molding (LIM) | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.13 | g/cm³ |
| Hardness | Nominal Value | Unit |
| Durometer Hardness | 68 | |
| Elastomers | Nominal Value | Unit |
| Tensile Stress (100% Strain) | 4.46 | MPa |
| Tensile Strength | 10.2 | MPa |
| Tensile Elongation (Break) | 420 | % |
| Tear Strength ¹ | 37.0 | kN/m |
| Compression Set (180°C, 22 hr) | 7.0 | % |

| Thermoset | Nominal Value | Unit |
|-------------------------------|---------------|------|
| Shelf Life (32°C) | 26 | wk |
| Post Cure Time (200°C) | 4.0 | hr |
| Additional Information | | |
| Press / Post Cure: Press/Post | | |
| Uncured Properties | Nominal Value | Unit |
| Curing Time | 0.083 | hr |
| NOTE | | |
| 1. | B mould | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

