

# StarTwist™ 315XM (metallized)

Cellulose Acetate

Innovia Films Ltd.

### Message:

Vinyl Coated Barrier Films for Packaging Applications  
Ultra high performance transparent or metallized twist film  
Literature reference: A350

General Information			
Features	Biodegradable		
	High Clarity		
	Renewable Resource Content		
Uses	Film		
	Packaging		
Appearance	Metallized - Clear		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Oxygen Transmission Rate (Wet) (23°C, 22 µm, 0.0% RH)	1.00	cm³/m²/24 hr	ASTM F1927
Water Vapor Transmission Rate (22 µm, 38°C, 90% RH)	10	g·mm/m²/atm/24 hr	ASTM E96
Film Gauge	21.9	µm	Internal Method
Yield (21.9 µm)	31.7	m²/kg	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT