

Petlon R-Prime B3-G15-00-BK

Polyamide 66
Petlon Polymers Ltd

Message:
100% Recycled Nylon 66, 15% Glass Reinforced, Black Compound.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Recycled Content	Yes,100%		
Appearance	Black		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Molding Shrinkage	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	30	kJ/m ²	ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	70.0 to 120	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT