

SABIC® PPcompound G3240A

Polypropylene Homopolymer
Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PPCOMPOUND G3240A is a general purpose, 40% glass filled, chemically coupled, heat stabilized homopolymer polypropylene compound. The IMDS ID is 139448304.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Additive	heat stabilizer		
Features	Chemical coupling		
	Homopolymer		
	Thermal Stability		
Uses	General		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction: 23°C, 48 hours	0.80	%	Internal method
Flow direction: 23°C, 48 hours	0.40	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7610	MPa	ASTM D638
--	8900	MPa	ISO 527-2/1
Tensile Strength			
Fracture ²	120	MPa	ASTM D638
Fracture	111	MPa	ISO 527-2/1A/50
Tensile Elongation			
Fracture ³	2.4	%	ASTM D638
Fracture	2.9	%	ISO 527-2/50
Flexural Modulus			
64.0mm span ⁴	8900	MPa	ISO 178
50.0mm span ⁵	7810	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C ⁶	13	kJ/m ²	ISO 179/1eA
23°C ⁷	10	kJ/m ²	ISO 179/1eA
Notched Izod Impact			

23°C, 3.20 mm ⁸	98	J/m	ASTM D256
-30°C ⁹	11	kJ/m ²	ISO 180/1A
23°C ¹⁰	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact ¹¹ (23°C, 3.20 mm)	610	J/m	ASTM D4812
Instrumented Dart Impact ¹² (23°C, Energy at Peak Load)	4.34	J	ASTM D3763
Dart Drop Impact ¹³ (23°C)	0.380	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	161	°C	ASTM D648
0.45 MPa, not annealed ¹⁴	161	°C	ISO 75-2/B
1.8 MPa, unannealed, 3.20mm	153	°C	ASTM D648
1.8 MPa, not annealed ¹⁵	153	°C	ISO 75-2/A
Vicat Softening Temperature	164	°C	ISO 306/A50
Coefficient of Linear Thermal Expansion			ISO 11359-2
Flow: -30 to 100°C	16.7	µm/Mk	ISO 11359-2
Transverse: -30 to 100°C	155	µm/Mk	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	190 - 230	°C	
Middle Temperature	200 - 250	°C	
Front Temperature	210 - 270	°C	
Nozzle Temperature	210 - 270	°C	
Processing (Melt) Temp	210 - 270	°C	
Mold Temperature	15.0 - 60.0	°C	
Back Pressure	1.00 - 1.50	MPa	
NOTE			
1.	50 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	2.0 mm/min		
5.	1.3 mm/min		
6.	80*10*4mm, Cut		
7.	80*10*4 mm, Cut		
8.	63.5*12.7*3.2mm, Cut		
9.	80*10*4mm, Cut		
10.	80*10*4mm, Cut		
11.	63.5*12.7*3.2mm, Cut		
12.	2.20 m/sec		
13.	0.625"d tup		
14.	80*10*4mm, Cut		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

