Hostacom EKC 425N C11323

Polypropylene

LyondellBasell Industries

Message:

Hostacom EKC 425N is a 15% mineral filled impact polypropylene compound.

The grade exhibits a good balance Stiffness / Impact & offers good Surface Appearance with an excellent Scratch Resistance. The product is designed and suitable for automotive Interior Applications requiring Low Emission / Low odour performances.

Typical applications are injected Instrument Panels.

This grade is available in custom colour, pellet form.

| General Information | | | |
|---------------------------------------|------------------------------|----------|-------------|
| Filler / Reinforcement | Mineral,15% Filler by Weight | | |
| Features | Good Impact Resistance | | |
| | Good Stiffness | | |
| | Good Surface Finish | | |
| | Low Emissions | | |
| | Low to No Odor | | |
| | Scratch Resistant | | |
| Uses | Automotive Applications | | |
| | Automotive Instrument Panel | | |
| Appearance | Colors Available | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.02 | g/cm³ | ISO 1183/A |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 13 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 1900 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact Strength | | | ISO 180/1A |
| -30°C | 5.0 | kJ/m² | |
| 23°C | 25 | kJ/m² | |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature | | | |
| 0.45 MPa, Unannealed | 100 | °C | ISO 75-2/B |
| 1.8 MPa, Unannealed | 56.0 | °C | ISO 75-2/A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

