

MAXAMID™ 7055 BK100

Polyamide 66

Pier One Polymers, Inc.

Message:

MAXAMID™ 7055 BK100 is a 55% glass fiber reinforced nylon 66 offering an excellent balance of high temperature performance, dimensional stability, tensile strength and impact resistance.

General Information			
Filler / Reinforcement	Glass Fiber,55% Filler by Weight		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	High Heat Resistance		
	High Tensile Strength		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.56	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	214	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	12400	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	254	°C	ASTM D648
Peak Melting Temperature	261	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.20	%	
Processing (Melt) Temp	288 to 304	°C	
Mold Temperature	65.6 to 98.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

