

VERSIFY™ 3200

Plastomer

The Dow Chemical Company

Message:

VERSIFY™ 3200 Plastomer is a resin with a medium melt flow rate, therefore making it a general purpose film resin. It is suitable for cast film, blown film, and BOPP and is an excellent sealant. It has excellent compatibility with PP, excellent adhesion to PE and is an useful agent to bring low seal initiation temperature, softness and temperature performance.

Main Characteristics

Pellet
Medium Melt Flow Rate

Good sealant
Compatible with PP
Soft polypropylene

Applications
Blown Film

Cast Film
BOPP

Sealant
Complies with:

EU, No 10/2011
U.S. FDA FCN 909
U.S. FDA 21 CFR 175.105(c)(5)

Consult the regulations for complete details.

General Information			
Agency Ratings	EU No 10/2011		
	FDA 21 CFR 175.105(c) (5)		
	FDA FCN 909		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.876	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Total Crystallinity	30	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness ¹			ASTM D2240
Shore A, Compression Molded	94		
Shore D, Compression Molded	44		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, Compression Molded)	22.1	MPa	ASTM D638
Tensile Elongation ² (Break, Compression Molded)	840	%	ASTM D638
Flexural Modulus - 1% Secant (Compression Molded)	131	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method

Glass Transition Temperature	-23.0	°C	Internal Method
Vicat Softening Temperature	59.0	°C	ASTM D1525
Melting Temperature (DSC)	85.0	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Gardner Gloss			ASTM D523
20°, 1000 µm, Compression Molded	125		
60°, 1000 µm, Compression Molded	134		
Haze (2000 µm, Injection Molded)	3.9	%	ASTM D1003
NOTE			
1.	Hardness after 10 seconds.		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

