

# apilon 52® F-60L

Thermoplastic Polyurethane Elastomer (Polyester)

API SpA

Message:

apilon 52®F-60L is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) product. It can be processed by injection molding and is available in Europe. apilon 52®F-60L application areas include engineering/industrial accessories, electrical/electronic applications, electrical appliances, tools and home applications.

- Features include:
- environmental protection/green
  - Good processability
  - Rapid Prototyping Cycle
  - Good UV resistance
  - low temperature resistance

General Information			
Features	Good UV resistance		
	Recyclable materials		
	Workability, good		
	Fast molding cycle		
	Low temperature resistance		
	Hydrolysis resistance		
Uses	Handle		
	Wheels		
	Conveyor belt repair		
	Electrical/Electronic Applications		
	Electrical appliances		
	Washer		
	Power/other tools		
	Pipe fittings		
	Household goods		
	Sporting goods		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 3 sec)	56		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	37.0	MPa	ASTM D638

100% strain	13.0	MPa	ASTM D638
300% strain	24.0	MPa	ASTM D638
Tensile Elongation (Break)	550	%	ASTM D638
Flexural Modulus (23°C)	170	MPa	ASTM D790
Abrasion Resistance	30.0	mm <sup>3</sup>	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>1</sup>	115	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-20°C)	160	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	80 - 100	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	185 - 200	°C	
Front Temperature	190 - 215	°C	
Nozzle Temperature	200 - 230	°C	
Mold Temperature	30 - 60	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Slow-Moderate		
NOTE			

1. With Notch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

