

4DUR® 9K22120 FR1

Polybutylene Terephthalate
4Plas

Message:

4DUR 9K22120 FR1 is a Standard Flow 20% Glass Fibre Reinforced FR-V0 PBT

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.58	g/cm ³	ISO 1183
Molding Shrinkage			
Vertical flow direction	1.1	%	
Flow direction	0.30	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	120	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	9.0	kJ/m ²	ISO 179/1eA
	50		
Charpy Unnotched Impact Strength (-30°C)			
	40	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	7.0	kJ/m ²	ISO 180/1A
23°C	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	55	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	210	°C	ISO 75-2/A
Vicat Softening Temperature	204	°C	ISO 306/B
Melting Temperature ²	225	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093

Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.040	%	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	60.0 - 100	°C	
Injection Rate	Fast		
Holding Pressure	40.0 - 80.0	MPa	
Screw Speed	200	rpm	
Injection instructions			
Feed Throat Temperature: 50 - 70 °C Back Pressure: Low			
NOTE			
1.	24 Hrs		
2.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

